

TECHNICAL SPECIFICATION CENOSPHERE GRADE - VA-SP-150

VA-SP-150

Typical Properties of CENOSPHERE

Al ₂ O ₃	32 - 38%
SiO ₂	55 - 68%
Fe ₂ O ₃	1 - 4%
K ₂ O	1.2 - 3.2%
TiO ₂	0.8 - 1.3%
MgO	1 - 2.5%
Na ₂ O	0.2 - 0.6%
CaO	0.1 - 0.5%
Co ₂	70%
N ₂	30%

Physical Properties CENOSPHERE

Specific Gravity (g/cc)	0.75 - 0.90
Bulk Density (KG/M ³)	315 - 400
Sinkers	5 - 9% Max.
Compressive Strength	180 - 280 KGS/CM ² (3000 PSI)
Hardness (Moh's)	5 - 6
Shape	Spherical
Color	Grey, Light or Dark Grey - Light Buff
Melting Point	1200 - 1400 DEG CELCIUS
PH in water	6 - 7
Moisture	0.5% Max
Oil Absorption	16-18 G/100G
Packing Factor	60 - 65 %
Thermal Conductivity	0.11WM-1K-1
Loss On Ignition	1 to 2% Max.
Wall Thickness	5 - 12 % of SHELL DIAMETER

SEIVE ANALYSIS OF CENOSPHERE VA-SP-150

MORE/LESS	B.S.S.	MICRONS	PERCENTAGE %
MORE THEN	52	300	NIL
MORE THEN	100	150	2 - 5%
MORE THEN	150	106	55 - 65%
MORE THEN	240	63	75 - 90%
LESS THEN	240	63	10 - 25%

WE CAN MAKE REQUIRED CHANGES IN THE GRADE AS PER YOUR REQUIREMENTS.

Mumbai Office :

703, Nav Renuka, Plot No. 108
Tilak Road, Opp. Balaji Mandir Road
Ghatkopar (East), Mumbai - 400077

Factory :

Beside Bhaskar Exxcoils Pvt. Ltd.
Village - Wadoda, Bhandara Road
Tal. Kamphthi, Dist. Nagpur - 441104

T : 022 - 2102 6172
M : +91 - 98211 62079
E : kulincorporation@gmail.com